

## Technical Information Putty for windows

---



DUPLI-COLOR Putty for Windows ist excellently suitable for single glazings and repairs.

### Quality and properties

---

- Permanent control of raw material and a long-years experience grant safety and constant quality.
- In case of single glazing there occurs the well-known building of condense water in direction to the room. It has to be avoided that this water infiltrates the putty.

### Physical and chemical data

---

- **Basis of the binder:** linseed oil
- **Colour:** beige
- **Storage stability:**  
12 months if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%) in the unopened original container.  
Do not store below 5°C
- **Size:** plastic container with 500 ml

### Environment and labelling

---

**Environmentally compatible:** European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal:** Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse".

*Only for DE: In order to ensure a high reuse and recycling rate, the legislator requires, in accordance with §15 - VerpackG, Paragraph 1, the return of transport, sales or outer packaging, alternatively, however, deviating agreements can also be made.*

**Labelling:** All products of European Aerosols comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals** (GHS) or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

### Using instructions

---

**Before use, carefully read and observe the warning texts on the label!**

#### Treatment:

- Glass folds have to be clean, dust-free and dry.
- Before puttying prime film-forming.

#### After treatment:

- Because of it's surface which is not weather-stable, the putty has to be protected by a coating. Earliest after skinning, latest after 4-8 weeks is has to be coated. Too early coating can lead to wrinkling.
- Can be overpainted with the most alkyd lacquers. At water-thinnable paints there might occur incompatibility by discolouration resp. fissures. We recommend tests.

### Order information

---

#### Disclaimer of liability

---

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of March 12, 2018

This release replaces all eventually earlier issued versions.

Print date: 27.04.2024

European Aerosols GmbH | Kurt-Vogelsang-Straße 6 | 74855 Haßmersheim | [info-de@european-aerosols.com](mailto:info-de@european-aerosols.com)