

Technical Information Putty for Wood



presto Putty for wood "styrene-free" is a 2-component repair-putty. With presto Putty for wood "styrene-free", small and medium damages on wooden surfaces can be closed durably. The coloured putty levels holes and deep scratches in all types of wood.

Colours: beech (brown), oak (dark brown), maple (light brown)

Universal use in the entire field of hobby and do-it-yourself.

Quality and properties

- Ease of working
- High elasticity
- Good adherence
- Easy to sand, even after a longer period
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt

Physical and chemical data

- **Basis:** polyester resin with mineral fillers
- **Colour:** light brown, medium brown, dark brown
- **Smell:** characteristic
- **Consistence:** soft, thixotropic
- **Pot life / Working time at 20°C:** approx. 7 - 8 minutes
- **Working temperature:** min. 12°C
- **Drying time (at 20°C, 50% relative air humidity):** can be sanded after approx. 30 - 40 minutes
- **Flash point:** approx. 33°C (resin); not applicable for hardener
- **Density at 20°C:**
putty 1.85 g/cm³
hardener 1.15 g/cm³
- **Addition of hardener:** 2 - 4 % (optimal mixture 2,5 %)
- **Temperature resistance of the cured material:** 120°C
- **Storage stability:**
18 months if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%) in the unopened original container. Protect from direct sunlight, frost and humidity.
- **Packing:**
Putty: small ring tins, 250 g; hardener: plastic tubes

Environment and labelling

Environmentally compatible: European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal: Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse".

Only for DE: In order to ensure a high reuse and recycling rate, the legislator requires, in accordance with §15 - VerpackG, Paragraph 1, the return of transport, sales or outer packaging, alternatively, however, deviating agreements can also be made.

Labelling: All products of European Aerosols comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals (GHS)** or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

Using instructions

Before use, carefully read and observe the warning texts on the label!

Application

- The object you wish to repair should be de-rusted, clean, dry, fat-free and sanded.
- Take the requested portion of putty compound out of the can and mix it well with the corresponding quantity of hardener.
- Apply the mixed material in the desired layer thickness.
- Clean tools immediately after use, if necessary with a nitro thinner.
- Do not return mixed material into the can.
- After approx. 30-40 minutes the repaired spot can be drilled, sanded, sawed, rasped and painted.

Order informations

Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of August 24, 2010

This release replaces all eventually earlier issued versions.

Print date: 29.04.2024

