

Technical Information Polyester Fine Filler "styrene-free"



Highly elastic, 2-component polyester fine filler to fill small unevennesses and for the "fine-filling" of pre-treated surfaces. Applicable on metal, wood, concrete and on repair spots which are filled with presto Body Filler. Micro-fine filling components result in a very smooth surface.

For universal use on many materials in the entire car, construction, and hobby sector.

For preparation and finishing your filling job, we recommend our presto sand papers. We offer a wide assortment of fine and coarse papers for dry and wet sanding.

Quality and properties

- Composition of highly-reactive, unsaturated polyester resin, filled with a new, micro-fine pigment-filler-combination
- Results in a very smooth surface
- Ease of working
- Easy to sand
- Very good adhesion
- Free of asbestos and silicone
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt

Physical and chemical data

- **Basis:** polyester resin with a pigment-filler-combination
- **Colour:** white
- **Smell:** characteristic
- **Consistence:** soft, thixotropic, pasty
- **Pot life / Working time at 20°C:** approx. 7 - 8 minutes
- **Working temperature:** min. 12°C
- **Drying time (at 20°C, 50% relative air humidity):** can be sanded after approx. 30 - 40 minutes
- **Flash point:** approx. 33°C (resin); not applicable for hardener
- **Density at 20°C:** putty 1.7 g/cm³
hardener 1.15 g/cm³
- **Addition of hardener:** 2 - 4 % (optimal mixture 2,5 %)
- **Temperature resistance of the cured material:** 120°C
- **Storage stability:** 18 months if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%) in the unopened original container. Protect from direct sunlight, frost and humidity.
- **Packing:** small ring tins; hardener: plastic tubes

Environment and labelling

Environmentally compatible: European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal: Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse".

Only for DE: In order to ensure a high reuse and recycling rate, the legislator requires, in accordance with §15 - VerpackG, Paragraph 1, the return of transport, sales or outer packaging, alternatively, however, deviating agreements can also be made.

Labelling: All products of European Aerosols comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals** (GHS) or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

Using instructions

Before use, carefully read and observe the warning texts on the label!

Application

- The object you wish to repair should be de-rusted, clean, dry, fat-free and sanded.
- As a primer before and after filling we recommend the [presto epoxy primer](#) (please note the drying time).
- Take the requested portion of putty compound out of the can and mix it well with the corresponding quantity of hardener.
- Apply the mixed material in the desired layer thickness.
- Clean tools immediately after use, if necessary with a nitro thinner.
- Do not return mixed material into the can.
- After approx. 30 - 40 minutes the repaired spot can be drilled, sanded, sawed, rasped and painted.
- presto Fine Filler is very elastic and constantly easy to sand.
- The putty can be applied to surfaces with low temperatures (minimum +5°C). The filler itself should have room temperature.
- Advise: do not apply directly on zinc-plated surfaces; these have to be primed before with a suitable zinc primer.

Order informations

Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of March 6, 2016
This release replaces all eventually earlier issued versions.

Print date: 30.04.2024

European Aerosols GmbH | Kurt-Vogelsang-Straße 6 | 74855 Haßmersheim | info-de@european-aerosols.com