

## Quality and properties

- Quick and easy working
- Quick drying allows quick working
- High elasticity
- Good adherence
- Easy to sand, even after a longer period
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt

## Physical and chemical data

- **Basis:** polyester resin with mineral fillers
- **Colour:** beige
- **Smell:** styrol
- **Consistence:** soft, thixotropic
- **Pot life / Working time at 20°C:** 60 minutes
- **Drying time (at 20°C, 50% relative air humidity):** can be sanded after 3 hours
- **Flash point:** approx. 33°C (resin); not applicable for hardener
- **Density at 20°C:** putty 1.5 g/cm<sup>3</sup>  
hardener 1.0 g/cm<sup>3</sup>
- **Addition of hardener:** 3 %
- **Temperature resistance of the cured material:** 120°C
- **Storage stability:** 18 months if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%) in the unopened original container. Protect from direct sunlight, frost and humidity.
- **Packing:** Filler: 1.5 kg tin  
Hardener: 50 ml plastic bottle

## Environment and labelling

**Environmentally compatible:** European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal:** Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse".

*Only for DE: In order to ensure a high reuse and recycling rate, the legislator requires, in accordance with §15 - VerpackG, Paragraph 1, the return of transport, sales or outer packaging, alternatively, however, deviating agreements can also be made.*

**Labelling:** All products of European Aerosols comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals** (GHS) or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

## Using instructions

**Before use, carefully read and observe the warning texts on the label!**

### Application

- The ground has to be clean, dry and free from fat.
- Mix the filler with the hardener well in the mentioned ratio.
- Work only with gravity spray gun
- Application in several wet-in-wet coats is possible.
- Spray pressure: 2 - 4 bar
- Jet size: 1.6 - 3.0 mm
- Before application of the finish coat you should apply a 2K primer, in order to avoid formation of "bubbles".
- Do not use directly on zink-plated surfaces, these have to be primed with a suitable zinc primer before.

## Order informations

### Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of march 22, 2021

This release replaces all eventually earlier issued versions.

Print date: 01.05.2024

European Aerosols GmbH | Kurt-Vogelsang-Straße 6 | 74855 Haßmersheim | [info-de@european-aerosols.com](mailto:info-de@european-aerosols.com)