

## Technical Information SPRAYPLAST Thinner



Special thinner for MoTip SPRAYPLAST peel-off lacquer. To set up the working viscosity for application with a spray gun and eventually necessary cleaning of spray gun or tools.

Which thinner you need, depends on the surrounding temperature and the size of the object to be painted.

For optimal paint results use the following thinner:

Thinner short: at temperatures of 10-25°C or for smaller paint-jobs, e.g. mirrors, small vehicle parts.

Thinner long: at temperatures >25°C or for bigger paint-jobs, e.g. whole vehicles and big vehicle parts.

### Quality and properties

- Contains medium and quick volatile solvents for dilution.
- The solvent mixture severely lowers the viscosity of the coating material, so that the ready for processing lacquer has a high solid contents.

#### Attention:

- Highly flammable liquid and vapour.
- Causes serious eye irritation.
- May cause drowsiness or dizziness

Please observe material safety data sheet!

### Physical and chemical data

- **Basis:** solvent
- **Smell:** solvent
- **Efficiency:**  
1000 ml thinner are sufficient to dilute 2000 ml of SPRAYPLAST lacquer
- **Storage stability:**  
5 years, if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%), storage in the closed, original container.
- **Disposal:**  
The product and the container have to be delivered to special waste disposal
- **Size:** tin cans, volume 1000 ml

### Environment and labelling

**Environmentally sound:** European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal:** Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

**Marking/Labelling:** All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

### Using instructions

**Before use, carefully read and observe the warning texts on the label!**

#### Application in a spray gun:

- Before use, dilute the lacquer with the SPRAYPLAST thinner in a 2 : 1 ratio.
- Prepare a max. quantity of 1.5 L ready mixed lacquer. Apply this within 20 - 30 minutes.
- For more information see label of the lacquer or on the technical data sheet of the SPRAYPLAST lacquer

### Order information

#### Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of January 22, 2016

This release replaces all eventually earlier issued versions.

Print date: 03.05.2024

European Aerosols | Wolfraamweg 2 | 8471 XC Wolvega | NL | [info-nl@european-aerosols.com](mailto:info-nl@european-aerosols.com)