

## Technical Information Ceramic Grease



Metal free ceramic grease with excellent adhesion, to treat parts which are liable to heavy workload and/or which are exposed to very high temperatures. Ceramic grease protects against electrolytic corrosion and has high thermal stability. Ceramic grease is resistant to chemicals, weather influences, water, salt and weak acids and bases. Ceramic grease prevents wear and sticking and has a directed jetspray. MoTip Ceramic Grease is extremely suitable to mount ABS brake systems and lambda sensors.

### For use on:

ABS and ASR brakes, lambda sensors and brake parts

## Quality and properties

- Protects against electrolytic corrosion
- High thermal stability
- Resistant to chemicals and weather influences
- Resistant to water, salt and weak acids and bases
- Excellent adhesion
- Prevents wear and sticking
- Extremely suitable to mount ABS brake systems and lambda sensors
- Directed jetspray
- Simplifies the future removal

## Physical and chemical data

- **Basis:** very fine ceramic particles
- **VOC-content:** approximately 68% w/w
- **Colour:** white
- **Smell:** characteristic
- **Appearance:** pasty
- **Relative density at 20°C:** 1.26 g/ml
- **Yield:** 1.65 g/sec.
- **Vapour pressure at 20°C:** 3 - 4 bar
- **Temperature resistance:** -40°C to + 1.200°C
- **Storage stability:**  
10 years if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%)
- **Size:**  
aerosol can, maximum nominal volume 500 ml

## Environment and labelling

**Environmentally sound:** European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal:** Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

**Marking/Labelling:** All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

## Instruction manuel

**Before use, carefully read and observe the warning texts on the label!**

### Application:

- Bring can to room temperature.
- Operating temperature 5° to 30°C.
- Shake for 2 minutes before use.
- Remove moisture, dirt and grease from part to be sprayed.
- Apply Ceramic Grease evenly and leave to dry.
- The specific properties are achieved after the solvent has evaporated (ca. 1 Minute).
- **Make sure the friction areas are not sprayed!**

## Tips for spray painting

Protect the object and the surrounding area from spray mist.  
Temperature should range between +10°C and +25°C, max. air humidity 60 %.

Store in a dry place. Protect from direct sunlight and other sources of heat. Use only during dry weather, in places protected from the wind, and in well-ventilated rooms. Follow the warning texts on the labels!

## Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of: October 31, 2011

This release replaces all eventually earlier issued versions.

Print date: 30.04.2024

European Aerosols | Wolframweg 2 | 8471 XC Wolvega | NL | [info-nl@european-aerosols.com](mailto:info-nl@european-aerosols.com)