

## Technical Information Rust Converter Spray



presto stop Rust Converter Spray is a rust converter and primer in one work step.

This rust restoration system on epoxy resin basis merges with the neutralized rust layer to a metallic-organic iron complex. This black, very compact protection layer builds the primer and is the basis for the subsequent, durable lacquer finish.

Excellently suitable for the restoration of vehicles, machines and all kinds of facilities.

Recommendation: our presto assortment offers the right putty for all purposes, e.g. the presto Body Filler for universal use.

### Quality and properties

- Anti-corrosive, reliable rust protection and rust converter
- Rust emerges into a water-insoluble, black, organic iron complex. This iron complex compound is stabilized by a special epoxy resin, which protects the iron from external influences.
- Air-drying
- Forms a perfect film
- Very good creeping
- Easy to spray on
- Compatible with all customary putties, fillers and lacquer finishes
- For use of 2-component lacquers we recommend a compatibility test
- Very good solvent-resistance
- Free of heavy metals and mineral acids
- No aggressive odour

### Physical and chemical data

- **Basis:** epoxy resin
- **Colour:** amber
- **Smell:** solvent
- **Efficiency:**  
Depending on consistence and colour of the ground  
150 ml are sufficient for approx. 0.6 m<sup>2</sup>  
400 ml are sufficient for approx. 1.6 m<sup>2</sup>
- **Drying time (at 20°C, 50% relative air humidity):**  
Dust-dry after approx. 1 hour  
Coatable: earliest after 6 hours ("finger nail dry")  
The drying time depends on temperature of surrounding area, air humidity and applied quantity.
- **Thickness of dry coat:** 40 - 50 µm in 3 - 4 coats
- **pH-value:** 4 - 4.5 after DIN 53785
- **Solid contents:** approx. 16 % after DIN 53216
- **Density:** 0.9 kg/dm<sup>3</sup> after DIN 53785
- **Viscosity (25°C):** approx. 37 centistokes
- **Temperature resistance:** permanent up to 80°C (short-term < 15 min 160°C)
- **Storage stability:**  
10 years if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%)
- **Packing:**  
Aerosol cans, max. nominal volume 150 ml resp. 400 ml

### Environment and labelling

**Environmentally sound:** European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal:** Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

**Marking/Labelling:** All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

### Using instructions

The most presto spray paints have a so-called no-spray ring or a tamper-proof cap. This is to avoid unauthorized use. Please see the corresponding advises on the cap or on the label.

**Before use, carefully read and observe the warning texts on the labels!**

### Application

- Remove rust, fat, dirt as well as paint flakes which are infiltrated by corrosion; use a brush if necessary.
- Before use, shake the can for approx. 2 minutes.
- Apply 3 - 4 layers, depending of degree of corrosion.
- Spray from a distance of approx. 25 cm.
- Coatable after approx. 6 hours, depending on ambient temperature.
- Additional stoving makes the protective coat especially resistant to water-, saltwater and solvents. Let the sprayed coat dry for 15 minutes, then stove for 15 minutes at 160°C.

### Tips for spray painting

Protect the object and the surrounding area from spray mist. When painting small areas it is recommended that a piece of card is used as a mask, with a hole cut in it slightly larger than the area to be sprayed. The mask should be held 1 to 2 cm from the surface. With this method, the mainly part of the spray mist is brought under control. It recommends to mask parts not to be lacquered, to protect the surrounding against the spray mist.

The aerosol can should have room temperature.

Temperature should range between +10°C and +25°C, max. air humidity 60 %.

Store in a dry place. Protect from direct sunlight and other sources of heat. Use only during dry weather, in places protected from the wind, and in well-ventilated rooms. Follow the warning texts on the labels!

#### **Disclaimer of liability**

---

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of June 24, 2014

This release replaces all eventually earlier issued versions.

Print date: 28.04.2024

European Aerosols | Wolfraamweg 2 | 8471 XC Wolvega | NL | [info-nl@european-aerosols.com](mailto:info-nl@european-aerosols.com)