

Technical information 1K Primer for Zinc



Specifieke additieven zorgen ervoor dat ColorMatic 1K Primer voor Zink een uitstekende hechting en corrosiebescherming biedt, met name voor blank met zink bekleed staal. Dit sneldrogende product is speciaal geformuleerd voor het overspuiten van OEM verzinkte carrosserieën.

Voordat u gaat werken met ColorMatic 1K primer voor zink, het oppervlak behandelen met [ColorMatic Siliconenverwijderaar Art. nr. 174469](#). Voor het beste resultaat raden wij aan de [ColorMatic 2K Hi-Speed Primer](#) te gebruiken zodra de 1K primer voor zink is opgedroogd. Daarna kunt u overschilderen met gemengde verven uit onze pre-fill systemen op water- of solventbasis.

Toepassing:

Ideaal voor spot repair en het overspuiten van onderdelen.

Quality and properties Physical and chemical data

- Excellent adhesion and corrosion prevention, especially on bare zinc-coated steel
- Specially formulated for refinishing OEM-plated zinc-coated car bodies
- Simple, time saving application
- Fast drying time
- Recoat with water-based and solvent-based ColorMatic coatings
- **Basis of binder:** specific mixture of resin
- **Colour:** light grey
- **Smell:** solvent
- **Efficiency:** 1 m²
- **Substrate:** bare zinc-coated metal, sanded. Sanded through areas on galvanised substrates
- **Temperature resistance:** to 90°C
- **Storage stability:** 10 years if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%)
- **Size:** Aerosol cans, maximum nominal volume 400 ml
- **VOC-value:** 259,3g

Disposal and labelling

Disposal: Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling: All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

Using instructions

Before use, carefully read and observe the warning texts on the label!

Applications

- Clean the surface thoroughly and sand
- Damaged area must be dry and free of dust and grease
- Clean undercoat with ColorMatic silicone remover no. 174 469

- Shake the can well for 2 minutes
- Carry out spray test
- Do not use on thermoplastic undercoats!

- **For professional use only**
- **Wear an appropriate respirator (recommended type A2/P3)**




2 min



Primer 1-2
= 10-20 μ



5-8 min



variable



approx. 15 cm



20°C=15 min

Order information

Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of July 23, 2010

This release replaces all eventually earlier issued versions.

Print date: 16.08.2026

European Aerosols | Wolfraamweg 2 | 8471 XC Wolvega | NL | info-nl@european-aerosols.com