

Technical information 2K Hi-Speed Clear Coat, Glossy



ColorMatic 2K blanke lak is een hoogglanzende, extreem krasbestendige 2-componenten blanke lak met een zeer hoge weerstand tegen benzine, UV-stralen en weersinvloeden. Door de snelle droogtijd, zeer goede vloeï en eenvoudige polijstbaarheid is ColorMatic 2K blanke lak bijzonder geschikt voor spotrepair. Gebruik ColorMatic spot blender voor spot reparaties. ColorMatic pre-fill producten kunnen na 30 minuten droogtijd worden overgelakt. De vorige lak moet volledig droog zijn.

Toepassing:

Ideaal voor spotrepair en het overspuiten van onderdelen.

Klik [hier](#) voor een video demonstratie van de 2K technologie.

Quality and properties Physical and chemical data

- High-gloss, extremely scratch-resistant 2-component clear coat with very high resistance to petrol, UV rays and weathering
- Safe long-term corrosion and oxidation protection on metal substrates such as steel, zinc, aluminum, copper, brass, as well as ground and brushed stainless steel
- Long pot life
- Fast drying time
- Very good flow
- Easy to polish
- Best to use 200 ml can to avoid surplus
- **Basis of binder:** Acrylic
- **Colour:** transparent
- **Smell:** solvent
- **Degree of gloss:** (at measurement angle 60° acc. to DIN 67530?)
glossy: 85 gloss-units
- **Efficiency:**
Depending on consistence and colour of the ground:
200 ml are sufficient for approx. 0,3 - 0,4 m²
500 ml are sufficient for approx. 0,8 - 1,0 m²
- **Substrate:**
solvent- and water-based base coats
- **Drying time (at 20°C, 50% relative air humidity):**
Dust-dry: approx. 5 minutes
Dry to touch: approx. 5 hours
Hard-dry: 12 hours
Polishable: 7 hours
Coatable: 12 hours
The drying time depends on surrounding temperature, air humidity and thickness of the applied coat.
- **Temperature resistance:** to 120°C
- **Storage stability:**
36 month if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%)
- **Size:**
2 components aerosol cans, maximum nominal volume 200 and 500 ml
- **VOC-value:** 118,6g
- **Pot-life:**
24 hours at room temperature (20 - 25°C)

Disposal and labelling

Disposal: Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling: All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

Using instructions

Before use, carefully read and observe the warning texts on the label!

- Base coatings can be recoated with ColorMatic 2K hi-speed clear coat after drying for 30 minutes
- 2-3 full coats, 50µ
- Leave to dry for 2 minutes between coats

Mixing A components with hardener:

- Remove the protection cap from the bottom of the can and pull the pin out fully with the help of the inserted ring. This will release the knife, which will penetrate the wall of the aluminium cartridge.
- The cartridge will then rotate 360 °, be completely open and release the hardener.
- Shake the can vigorously to mix the A components with the hardener in the proper, predetermined ratio.
- Shake can vigorously for 2 minutes
- Carry out spray tests
- Pot life: 24 hours (20 ° C)


Ready-to-use coating materials containing isocyanates can irritate the respiratory system and cause allergic reactions. There is a risk of sensitization with inhalation of vapours and spray mist. When dealing with substances containing isocyanates, you should observe all guidelines for using solvent-based coatings. In particular, spray mist and vapours should not be inhaled. Allergy and asthma sufferers and people who are prone to respiratory diseases should not work with isocyanates materials.

- For professional use only
- Wear an appropriate respirator (recommended type A2/P3)

Hints concerning application

For an optimal coating result bring can to temperature prior to use (20 - 25 °C) and a relative air humidity of 45 - 60%.

Please note: a high air humidity can cause loss of gloss.







60°C=40 min
20°C= 7 h



25 min



20°C=7 h
60°C=45 min
IR=30 min



at 190469



Order information

Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. European Aerosols is let off the liability, unless the liability-based incident is caused by a fault incurred to European Aerosols.

As of February 17, 2020

This release replaces all eventually earlier issued versions.

Print date: 16.08.2026

European Aerosols | Wolfraamweg 2 | 8471 XC Wolvega | NL | info-nl@european-aerosols.com